

IP-100


Polypropylene Impact Copolymer

IP-100 is a Medium-Impact INJECTION MOLDING certified prime resin specially designed for applications requiring good impact resistance at low temperatures. **IP-100** features very good processability, medium-high flow for fast mold filling, excellent heat resistance, very good dimensional stability and optimal balance of mechanical properties. Recommended processing temperature is between 210 - 220°C. **IP-100** complies with FDA regulation 21CFR 177.1520 (a)(3)(i) / (c)3.1 + 3.2, and with most international regulations concerning the use of Polypropylene in contact with food articles.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
PHYSICAL			
Melt Flow Rate (230°C, 2.16kg)	D1238	g/10 min	10
Density	D1505	g/cm ³	0.902
Rockwall Hardness (R-Scale) Inj. Mold	D785		100
MECHANICAL			
Flexural Modulus ¹ (1% Secant)	D790	psi	150k
Tensile Strength @ Yield ²	D638	psi	3500
Notched Izod Impact (73°F)	D256	ft-lb/in	2.5
Tensile Elongation @ Yield ²	D638	%	7.0
Deflection Temperature Under Load (66 psi Unannealed)	D648	°F	185

Typical Value of Properties not to be construed as specifications

- 1 - @ 0.051 in/min
- 2 - @ 2 in/min.



Genesis Polymers

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.