

HD53-2000

High Density Polyethylene

HD53-2000 is a Hexene copolymer certified prime grade designed for injection molding, general purpose applications. **HD53-2000** features easy processability, good impact strength and good toughness. **HD53-2000** complies with FDA regulation 21CFR 177.1520(c) 3.2a.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
RESIN			
Melt Flow Rate (190 °C, 2.16kg)	D1238	g/10 min	20
Density	D1505	g/cm ³	0.953
Env. Stress Cracking Resistance (F50)	D1693B	hr	<10.0
MOLDED SPECIMEN			
Flexural Modulus (1% Secant)	D790B	psi	170k
Tensile Strength @ Yield ²	D638	psi	3830
Elongation @ Break ²	D638	%	280
HDT @ 66 psi (Under Load)	D648	°F	164
Brittleness Temperature	D746	°F	<-103
Vicat Softening Temperature	D1525	°F	250

Typical Value of Properties not to be construed as specifications

2 - @ 2 in/min.



The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.