

HD50-3500 High Density Polyethylene

HD50-3500 Is a narrow molecular weight Hexene Copolymer designed to maximize injection molding speed and productivity in thin wall articles. Lower processing temperatures enable production of products free of taste and odor for food and beverage packaging. **HD503500** complies with FDA regulation 21CFR 177.1520 (c) 3.1 (a) + 3.2 (a) and with most international regulations concerning the use of Polyethylene in contact with food articles.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
PHYSICAL			
Melt Flow Rate (190 °C, 2.16kg)	D1238	g/10 min	33
Density	D1505	g/cm ³	0.950
MECHANICAL			
Flexural Modulus ¹	D790	MPa	1200
Tensile Strength @ Yield ²	D638	MPa	24
Elongation @ Break ²	D638	%	>20
ESCR	D1693	Hr	1.00
Notched Izod Impact	D256	ft-In/in	.42
Deflection Temperature Under Load	D648	°C	71

Typical Value of Properties not to be construed as specifications

* Test Made on injection molded Type 1 tension test specimen according to ASTM D2146

1 - @ 0.051 in/min

2 - @ 2 in/min.



Genesis Polymers

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.